S20 NON-METALLIC PUMP TECHNICAL DATA SHEET

SERIES

STANDARD DUTY BALL VALVE PUMPS

Offering the widest range of performance and application capabilities

PERFORMANCE

SUCTION / DISCHARGE PORT SIZE

· 2" Universal Flange (Fits ANSI & DIN Flange)

CAPACITY

0 to 160 GPM (0 to 605 LPM)

AIR DISTRIBUTION VALVE

· No-lube, no-stall design

SOLIDS-HANDLING

Up to .66 in. (17mm)

HEADS UP TO

· 100 psi or 231 ft. of water (7 bar or 70 meters)

MAXIMUM OPERATING PRESSURE


100 psi (7 bar)

DISPLACEMENT/STROKE


· .46 Gallon / 1.73 liter

WEIGHTS

- Polypropylene 95 lbs. (43kg)
- PVDF 130 lbs. (59kg)
- · Conductive Polypropylene 100 lbs. (45kg)



DIMENSIONS





5 YEAR LIMITED PRODUCT WARRANTY

5 Year Guarantee for defects in material or workmanship. See sandpiperpump.com/content/warranty-certifications for complete warranty, including terms and conditions, limitations and exclusions.



USE ONLY GENUINE SANDPIPER PARTS

All certification, standards, guarantees & warranties originally supplied with this pump will be invalidated by the use of service parts not identified as "Genuine SANDPIPER Parts.














EXPLANATION OF PUMP NOMENCLATURE



PUMP BRAND

SANDPIPER®

PUMP SIZE

CHECK VALVE TYPE

Ball

DESIGN LEVEL

Design Level

WETTED MATERIAL

PV/DF

Polypropylene

Conductive Polypropylene

DIAPHRAGM/CHECK VALVE MATERIALS

Santoprene/Santoprene PTFE-Santoprene Backup/PTFE

PTFE Pumping, PTFE-Neoprene Backup Driver/PTFE 6

Nitrile/Nitrile

FKM / PTFE

PTFE-Neoprene Backup/PTFE Santoprene/PTFE G

Neoprene/Neoprene

One-Piece Bonded/PTFE

CHECK VALVE SEAT

PVDF

Polypropylene

NON-WETTED MATERIAL OPTIONS

Carbon Filled Conductive Polypropylene

40%Glass Filled Polypropylene

40%Glass Filled Polypropylene w/PTFE Coated Hardware

PORTING OPTIONS

Universal Flange

(Fits ANSI & DĬN)

Dual Porting (ANSI) Top Dual Porting (ANSI)

Bottom Dual Porting (ANSI) 9

PUMP STYLE

with Electronic Leak Detection (110V)

with Electronic Leak Detection (220V) with Mechanical Leak Detection Е

M

Standard

with Visual Leak Detection

PUMP OPTIONS

None

Metal Muffler 6

KIT OPTIONS

None

10.30VDC Pulse Output Kit P0.

Intrinsically-Safe 5.30VDC 110/120VÁC 220/240 VAC

Pulse Output Kit 110/120 or 220/240VAC Pulse Output Kit

Solenoid Kit with 24VDC Coil

Solenoid Kit with 24VDC

Explosion-Proof Coil

Solenoid Kit with 24VAC/12VDC Coil

Solenoid Kit with 12VDC E3. Explosion-Proof Coil

Solenoid Kit with 110VAC Coil

Solenoid Kit with 110VAC

Explosion-Proof Coil

Solenoid Kit with 220VAC Coil Solenoid Kit with 220VAC

E7.

Explosion-Proof Coil

Solenoid Kit with 110VAC, 50 Hz E8.

Explosion-Proof Coil

Solenoid Kit with 230VAC, 50 Hz

Explosion-Proof Coil Stroke Indicator Pins Solenoid Kit with 12 VDC A1. ATEX Compliant Coil

Solenoid Kit with 24 VDC

ATEX Compliant Coil

Solenoid Kit with 110/120 VAC 50/60 Hz ATEX Compliant Coil

Solenoid Kit with 220/240 VAC

50/60 Hz ATEX Compliant Coil

MATERIALS

Material Profile:	Operating Temperatures:	
CAUTION! Operating temperature limitations are as follows:	Max.	Min.
CONDUCTIVE ACETAL: Tough, impact resistant, ductile. Good abrasion resistance and low friction surface. Generally inert, with good chemical resistance except for strong acids and oxidizing agents.	190°F 88°C	-20°F -29°C
EPDM: Shows very good water and chemical resistance. Has poor resistance to oils and solvents, but is fair in ketones and alcohols.	280°F 138°C	-40°F -40°C
FKM (FLUOROCARBON): Shows good resistance to a wide range of oils and solvents; especially all aliphatic, aromatic and halogenated hydrocarbons, acids, animal and vegetable oils. Hot water or hot aqueous solutions (over 70°F(21°C)) will attack FKM.	350°F 177°C	-40°F -40°C
HYTREL®: Good on acids, bases, amines and glycols at room temperatures only.	220°F 104°C	-20°F -29°C
NEOPRENE: All purpose. Resistance to vegetable oils. Generally not affected by moderate chemicals, fats, greases and many oils and solvents. Generally attacked by strong oxidizing acids, ketones, esters and nitro hydrocarbons and chlorinated aromatic hydrocarbons.	200°F 93°C	-10°F -23°C
NITRILE: General purpose, oil-resistant. Shows good solvent, oil, water and hydraulic fluid resistance. Should not be used with highly polar solvents like acetone and MEK, ozone, chlorinated hydrocarbons and nitro hydrocarbons.	190°F 88°C	-10°F -23°C
NYLON: 6/6 High strength and toughness over a wide temperature range. Moderate to good resistance to fuels, oils and chemicals.	180°F 82°C	32°F 0°C

POLYPROPYLENE: A thermoplastic polymer. Moderate tensile and flex strength. Resists stong acids and alkali. Attacked by chlorine, fuming nitric acid and other strong oxidizing agents.	180°F 82°C	32°F 0°C
PVDF: (Polyvinylidene Fluoride) A durable fluoroplastic with excellent chemical resistance. Excellent for UV applications. High tensile strength and impact resistance.	250°F 121°C	0°F -18°C
SANTOPRENE®: Injection molded thermoplastic elastomer with no fabric layer. Long mechanical flex life. Excellent abrasion resistance.	275°F 135°C	-40°F -40°C
UHMW PE: A thermoplastic that is highly resistant to a broad range of chemicals. Exhibits outstanding abrasion and impact resistance, along with environmental stress-cracking resistance.	180°F 82°C	-35°F -37°C
URETHANE: Shows good resistance to abrasives. Has poor resistance to most solvents and oils.	150°F 66°C	32°F 0°C
VIRGIN PTFE: (PFA/TFE) Chemically inert, virtually impervious. Very few chemicals are known to chemically react with PTFE; molten alkali metals, turbulent liquid or gaseous fluorine and a few fluoro-chemicals such as chlorine trifluoride or oxygen difluoride which readily liberate free fluorine at elevated temperatures.	220°F 104°C	-35°F -37°C

Maximum and Minimum Temperatures are the limits for which these materials can be operated. Temperatures coupled with pressure affect the longevity of diaphragm pump components. Maximum life should not be expected at the extreme limits of the temperature ranges

Metals:

ALLOY C: Equal to ASTM494 CW-12M-1 specification for nickel and nickel alloy.

STAINLESS STEEL: Equal to or exceeding ASTM specification A743 CF-8M for corrosion resistant iron chromium, iron chromium nickel and nickel based alloy castings for general applications. Commonly referred to as 316 Stainless Steel in the pump industry.

For specific applications, always consult the Chemical Resistance Chart.



NOTE: See service manual for ATEX details.

